1. (Currently Amended) A varnish comprising:

an insulation resin,

a curing agent,

a flame retardant comprising, a salt of a basic nitrogenous compound with phosphoric

acid that is dispersible as solid particles in an organic solvent, surface treated with at least one

surface treatment agent selected from the group consisting of a phosphorus compound soluble in

an organic solvent, an organopolysiloxane, and a dispersant having a carboxyl group,

and an organic solvent, wherein said flame retardant comprises flame retardant particles

surface treated with at least one surface treatment agent selected from the group consisting of a

phosphorus compound soluble in an organic solvent, an organopolysiloxane and a dispersant

having a carboxyl group, and wherein said flame retardant comprises a salt of a basic

nitrogenous compound with phosphoric acid that is dispersible as solid particles in an organic

solvent.

2. (Previously Presented) The varnish according to claim 1, wherein said surface

treated flame retardant particles have a primary particle average major axis of 0.01 to 5 µm and

an average aspect ratio of up to 5 and contain up to 10% by number of particles having a major

axis of greater than 10 µm.

3. (Previously Presented) The varnish according to claim 1, wherein said surface

treated flame retardant particles are dispersed as particles having a secondary particle diameter of

up to 30 μm in the varnish.

2

MSW/CAM/amm

Application No. 10/511,143 Amendment dated September 18, 2007 After Final Office Action of April 19, 2007

Amendment dated September 18, 2007

4. (Previously Presented) The varnish according to claim 1, wherein said surface

treated flame retardant particles are obtained by surface treatment of the salt of a basic

nitrogenous compound with phosphoric acid by contact with a surface treatment agent in an

organic solvent, wherein said salt of a basic nitrogenous compound with phosphoric acid is wet

milled as needed.

5. (Canceled)

6. (Original) The varnish according to claim 1, wherein said phosphorus compound

soluble in an organic solvent is an alkyl acid phosphate with an alkyl group having at least 8

carbon atoms.

7. (Previously Presented) The varnish according to claim 1, wherein said

organopolysiloxane is an organopolysiloxane having a functional group selected from the group

consisting of an amino group, an epoxy group, a carboxyl group, an acrylate group, a

methacrylate group, a hydroxyl group, a mercapto group, a vinyl group, and a halogen atom.

3

MSW/CAM/amm

Docket No.: 4770-0103PUS1

8. (Currently Amended) The varnish according to claim 1, wherein said dispersant having a carboxyl group is a high-molecular weight dispersant having a structure in which the carboxyl group is bonded to a high-molecular weight compound selected from the group consisting of a polyester resin, an acrylic resin, a polyurethane resin, a polyether resin, and an alkyd resin.

- 9. (Previously Presented) The varnish according to claim 1, wherein said insulation resin is at least one insulation resin selected from the group consisting of an epoxy resin, a maleimide resin, a (meth) acrylic resin, a diallyl phthalate resin, a triazine resin, an alicyclic olefin polymer, an aromatic polyether polymer, a benzocyclobutene polymer, a cyanate ester polymer, a liquid crystal polymer, and a polyimide resin.
- 10. (Previously Presented) The varnish according to claim 9, wherein said alicyclic olefin polymer is an alicyclic olefin polymer having a polar group selected from the group consisting of a hydroxyl group, a carboxyl group, an alkoxyl group, an epoxy group, a glycidyl group, an oxycarbonyl group, a carbonyl group, an amino group, an ester group, and a carboxylic anhydride group.
- 11. (Currently Amended) The varnish according to claim 1, which contains, per 100 parts by weight of the insulation resin, 1 to 100 parts by weight of the curing agent and 0.1 to 80 parts by weight of the surface treated flame retardant particles, and further contains an organic

Application No. 10/511,143

Amendment dated September 18, 2007

After Final Office Action of April 19, 2007

solvent in an amount enough-sufficient to uniformly disperse or dissolve the insulating resin, the

curing agent and the flame retardant therein.

12. (Currently Amended) A formed material, which is obtained by applying and

drying a varnish of claim 1 on a substrate, wherein said varnish comprises (a) an insulation resin,

(b) a curing agent, (c) flame retardant particles surface treated with at least one surface treatment

agent selected from the group consisting of a phosphorus compound soluble in an organic

solvent, an organopolysiloxane and a dispersant-having a carboxyl group, and (d) an organic

solvent, and wherein said flame retardant comprises a salt of a basic nitrogenous compound with

phosphoric acid that is dispersible as solid particles in an organic solvent.

13. (Original) The formed material according to claim 12, which is a film or sheet.

14. (Original) An electrical insulation film, which is obtained by curing the film or

sheet according to claim 13.

15. (Original) A multilayer structure, wherein an electrical insulation layer obtained

by curing the formed material according to claim 12 is formed on a substrate having a conductor

circuit layer.

5

MSW/CAM/amm

Application No. 10/511,143

Amendment dated September 18, 2007

After Final Office Action of April 19, 2007

16. (Original) The multilayer structure according to claim 15, wherein said electrical

insulation layer is an electrical insulation film formed by thermocompression of the film or sheet

according to claim 13 on a substrate having a conductor circuit layer.

17. (Currently Amended) A process for preparing a surface treated flame retardant

particle comprising:

bringing into contact, wherein a flame retardant, comprising a salt of a basic nitrogenous

compound with phosphoric acid that is dispersible as solid particles in an organic solvent, is

brought in contact with and at least one surface treatment agent selected from the group

consisting of a phosphorus compound soluble in an organic solvent, an organopolysiloxane and a

dispersant having a carboxyl group in an organic solvent for surface treatment, wherein said

flame retardant is wet milled as needed, and wherein said flame retardant comprises a salt of a

basic nitrogenous compound with phosphoric acid that is dispersible as solid particles in an

organic solvent.

18. (Currently Amended) A flame retardant slurry, wherein flame retardant particles

comprising, a salt of a basic nitrogenous compound with phosphoric acid that is dispersible as

solid particles in an organic solvent, surface treated with at least one surface treatment agent

selected from the group consisting of a phosphorus compound soluble in an organic solvent, an

organopolysiloxane, and a dispersant having a carboxyl group, are dispersed in an organic

<u>solvent.</u>

6

MSW/CAM/amm

Docket No.: 4770-0103PUS1

surface treated with at least one surface treatment agent selected from the group

consisting of a phosphorus compound soluble in an organic solvent, an organopolysiloxane and a

dispersant having a carboxyl group are dispersed in an organic solvent, and wherein said flame

retardant comprises a salt of a basic nitrogenous compound with phosphoric acid that is

dispersible as solid particles in an organic solvent.

19. (Original) The flame retardant slurry according to claim 18, wherein said surface

treated flame retardant particles are dispersed as particles having a primary particle average

major axis of 0.01 to 5 µm and an average aspect ratio of up to 5 and containing up to 10% by

number of particles having a major axis of greater than 10 µm.

20. (Currently Amended) A varnish preparation process comprising:

a step (1) of preparing-surface treated flame retardant particles by bringing a flame retardant

comprising a salt of a basic nitrogenous compound with phosphoric acid that is dispersible as

solid particles in an organic solvent in contact with at least one surface treatment agent selected

from the group consisting of a phosphorus compound soluble in an organic solvent, an

organopolysiloxane and a dispersant having a carboxyl group in an organic solvent for surface

treatment, wherein said flame retardant is wet milled as needed, and

a step (2) of mixing together a flame retardant slurry in which mixing the surface treated

flame retardant particles are dispersed in an organic solvent, an insulation resin and a curing

agent, optionally followed by adding an organic solvent, and wherein said-flame retardant

7

Application No. 10/511,143 Amendment dated September 18, 2007 After Final Office Action of April 19, 2007 Docket No.: 4770-0103PUS1

comprises a salt of a basic nitrogenous compound with phosphoric acid that is dispersible as solid particles in an organic solvent.

21-25. (Canceled)